



FO-1,5

DONNEES TECHNIQUES	
Référence	FO-1,5

Product parameter: <ul style="list-style-type: none"> ◆ Fiber Core Material PMMA ◆ Fiber Cladding Material Fluorinated Polymer ◆ Core refractive index 1.492 ◆ Numerical Aperture 0.5 ◆ Number of Fiber 1 ◆ Minimum Bend Radius 30mm 		
---	--	--

Specifications:

	Item	Unit	Specification	Test Condition
Structural parameters	Core diameter	μm	1470±90	JIS C 6862
	Cladding diameter	μm	1500±90	
	Cladding non-circularity	%	≤6	
	Approximate Weight	g/m	2.2	
Optical properties	Transmission Loss	dB/km	≤220	650nm (JIS C 6863)
	Transmission Loss Under 95%RH	dB/km	240	
Mechanical Characteristics	Repeated Bending Endurance	1000 Times	Loss Increment=<1dB	JIS C 6861
	Tensile Strength	N	126	
	Twisting Endurance	5Times	Loss Increment =<1dB	
	Impact Endurance	0.4N.m	Loss Increment =<1dB	